

NiZn FERRITE POWDER PRODUCTS

(TYPICAL CHARACTERISTICS)

PROPERTIES	READY-TO-PRESS					LOW SINTERING TEMPERATURE				FULLY SINTERED	
	BP860	BP850	BP125HR	BP125	BP40	LSF400	LSF220	LSF120	LSF50	FA100	FP350
Initial Permeability, μ_i	860	850	125	125	40	450	250	130	55	*	*
Q Factor (w/ 10 turns)	50	10	250	300	250	90	90	180	130	N/A	N/A
@ Frequency (MHz)	0.1	0.1	2	2	10	0.2	0.2	1	5		
Flux Density, Bs (Gauss)	3500	3000	3600	3000	2600	3150	3250	3500	3650	N/A	N/A
@ Field Strength (Oersted)	30	30	30	30	40	30	30	30	30		
Residual Flux Density, Br (G)	2100	1800	1600	1200	800	1800	1800	1950	2500	N/A	N/A
Coercive Force, Hc (Oersted)	0.45	0.40	2.6	1.6	4.2	2	2	3	6	N/A	N/A
Resistivity (Ω -cm)	10^8	10^5	10^8	10^8	10^7	N/A	N/A	N/A	N/A	10^{11}	10^9
Curie Temperature ($^{\circ}$ C)	160	140	350	350	450	150	150	200	350	140	350
Shrinkage (%)	15.5	14.0	14.0	10.5	10.5	15.5	15.5	15.5	15.5	-	-
Sintering Temperature ($^{\circ}$ C)	1220	1250	1250	1270	1250	900	900	900	900	-	-
Soak Time (Hours)	2	3	3	3	3	2	2	2	2	-	-

Rev. July 2016

- ◆ **Other specialty NiZn ferrites (initial permeability of 15 ~ 3000) and custom ferrite compositions are available upon request.**
- ◆ **RoHS Compliant! – No Lead (Pb) or Cadmium (Cd) was added to any of our products.**
- ◆ Characteristics presented are typical values but not guaranteed specifications.
- ◆ Physical properties can be adjusted to meet customer requirements.
- ◆ Electromagnetic characteristics were tested on toroids by means of HP4294A Precision Impedance Analyzer.
Pressed toroid dimension for sintering test: approx. 20.6 mm OD x 11.3 mm ID x 5.1 mm HT.
- ◆ Fully Sintered Loading Ferrite Powders:
Custom-made particle sizes are available; median size ranging from 10 ~ 20 μ m ground powders to 80 ~ 130 μ m spherical powders.
* Powder-loading ratio and density with binder/resin will greatly affect on inductance, attenuation and applicable frequencies.